



Gram Volunteers / Ward Volunteers and Village Secretariats / Ward Secretariats Department, Government of Andhra Pradesh

Corrigendum 2 for Selection of Agency for supply of Uniforms to Village and Ward Functionaries.

Date: 9th September 2021

SI No	Page / Section reference of the RFP	Relevant Content of RFP	Amendment / Clarification / Addendum
1.	Page No. 6 Executive Conditions	Supplies against a purchase order shall be completed within 15 days otherwise liquidated damages shall be levied by Department of GVWV & VSWS.	Supplies against a purchase order shall be completed within 60 days otherwise liquidated damages shall be levied by Department of GVWV & VSWS.
2.	Page No. 6 Executive Conditions	Delivery Place: The CEOs/JC(VWS&D) of ZPPs based on the number of Village - Ward Secretaries in the District. The cloth material should be packed Secretariat wise and to be bundled Mandal/ULB wise at supplier level only. (Mandal/ ULB wise secretariats list will be shared with the selected bidder).	Delivery Place: The Assembly Constituency Head Quarters. The cloth material should be packed 15,004 Secretariats wise (Gender Wise separate packs) (list secretariats wise will be shared with the selected bidder).
3.	Page No 8 Conditions for eligibility of firm	The bidder should be a Manufacturer /Dealer / Supplier /having Business of uniform cloth/ cloth and in doing procurement & supply related work for any Government state /central or PSU	The bidder should be a Manufacturer /Dealer / Supplier /having Business of uniform cloth/ cloth and in doing procurement & supply related work to institutions and experienced in dealing of fabric goods.
4.	Page No 8 Conditions for eligibility of firm.	The cumulative turnover of the firm should be not less than Rs.5.00 Cr for the last 3 financial years (FY 2021-20, 2019-20 and 2018-19).	The cumulative turnover of the firm should be not less than Rs.15.00 Cr for the last 3 financial years (FY 2021-20, 2019-20 and 2018-19).



Gram Volunteers / Ward Volunteers and Village Secretariats / Ward Secretariats Department, Government of Andhra Pradesh

SI No	Page / Section reference of the RFP	Relevant Content of RFP	Amendment / Clarification / Addendum
5.	Page No. 6 Scope Sl. No. 1 : Suiting Trovin Cloth	67%-33% 2/30*2/30, Dyed Yarn 58 Inch width Suiting Cloth – Cream	Addendum Technical Specifications of Cloth 67%-33% 2/30*2/30, Dyed Yarn 58 Inch width Suiting Cloth (And) All the specifications should be as per test report no. TC/LH/ST/335/2021-22 attached in the Appendix – IV of this Corrigendum
6.	Page No. 6 Scope Sl. No. 2 : Shirting Cloth	Blue with White stripe Heavy quality Shirting 36 Inch Mill item - Blue	Addendum Technical Specifications of Cloth Blue with White stripe Heavy quality Shirting 36 Inch Mill item (And) All the specifications should be as per test report no. TC/LH/ST/333/2021-22 attached in the Appendix – IV of this Corrigendum
7.	Page No. 6 Scope Sl. No. 3 : Bottom Cloth	Spun/Spun Fine Yarn 36 Inch width ladies bottom cloth - Cream	Addendum Technical Specifications of Cloth Spun/Spun Fine Yarn 36 Inch width ladies bottom cloth (And) All the specifications should be as per test report no. TC/LH/ST/334/2021-22 attached in the Appendix – IV of this Corrigendum



Gram Volunteers / Ward Volunteers and Village Secretariats / Ward Secretariats Department, Government of Andhra Pradesh




SI No	Page / Section reference of the RFP	Relevant Content of RFP	Amendment / Clarification / Addendum
8.	Page No. 6 Scope Sl. No. 4 : Chunny Cloth	Georgette Cloth Heavy Quality - Cream	Addendum Technical Specifications of Cloth Georgette Cloth Heavy Quality (And) All the specifications should be as per test report no. TC/LH/ST/336/2021-22 attached in the Appendix – IV of this Corrigendum



Gram Volunteers / Ward Volunteers and Village Secretariats / Ward Secretariats Department, Government of Andhra Pradesh

APPENDIX-IV (Cloth Detailed Specifications)

1. Suiting Trovin Cloth

 देशीय प्रयोगशाला वस्त्र समिति भारत सरकार, वस्त्र मंत्रालय सुल्तानपुर बिल्डिंग, पहली मंजिल, डी.नं. 10-1-1200, ए.सी. गार्ड्स, मासब टैंक रोड, हैदराबाद - 4. टेलिफोन : 040-23327153 ई मेल : hyd.tc@nic.in	REGIONAL LABORATORY TEXTILES COMMITTEE (Ministry of Textiles, Govt. of India) Textile Testing Services-Quality Cell UNI Building, D.No. 10-1-1200, 1st Floor, A.C. Guards, Masab Tank Road, Hyderabad - 500 004, Telefax : 040-23327153 email : hyd.tc@nic.in		
TEST REPORT (Format No. 14/18/Q3)			
Test Report No. TC/LH/ST/335/2021-22	Date : 09.09.2021		
Name and Address of the Customer	: The Additional Commissioner (Rural) O/o Commissioner & Director, GWW & VSWs Department, Plot No. 11, Nirman Bhavan, APIIC Colony, Vijayawada		
Sample forwarding letter No. & Date	: 1490545/2021/GSWS, Dated.03.09.2021		
Date of receipt of sample	: 06.09.2021		
Date of performance of tests	: 06.09.2021 to 09.09.2021		
Customer Sample No.	Sample description as declared by the customer	Sample colour	Lab. Sample No.
	Uniform Cloth -Suiting (Male)		CCO-1776
TEST RESULTS			
ULRTC92292100000421P			
Identification of Fibre (IS: 667:1981 RA 2017)	Warp Weft	Polyester + Viscose Polyester + Viscose	
% Composition (TC/Lab/PTM-02&03) (IS:3416: Part 1:1988 RA 2017) (On Clean dry mass with % additions for moisture)	Polyester Viscose	WARP- 70.2 29.8	WEFT- 65.4 34.6
Breaking Strength of Fabric (Kgf) (IS:1969 Part I 2009 RA 2014) (Ravelled Strip of 5 x 20 cms)	Warp Weft	120.8 87.0	
Count of the yarn removed from fabric(NeC) (TC/LAB/TM-02.Vr.02)	Warp Weft	14.3 ^s (2F) 14.6 ^s (2F)	
Threads/inch (IS:1963:2004RA:2014)	Warp Weft	62 56	
Mass/Sq.Meter(g) (TC/Lab/TM-03.Vr.02)Cond.		202.0	
Pilling Resistance : (IS:10971:Part I:2011:RA:2017) Avg. Rating		4	
Relaxation Shrinkage % (IS:2977:1989 RA 2016) ('-' Shrinkage; '+' Elongation)	Warp Weft	- 0.57 - 0.29	
 M. NATARAJAN Assistant Director (EP&DA)			
(Complaints, if any, are to be received within 45 days of issue of Test Report)			
Sample is not drawn by Textiles Committee, results relate only to the above sample's tested. This test report is not to be published in any form without the explicit written consent of Textiles Committee. (Remnant samples will be retained for 90 days from the date of receipt of sample)			
Abbreviations	Pilling Rating	Colour Fastness to (Using Grey Scale)	
NeC : English Count		Grey Scale	Colour Change Staining
Nm : Metric Count	Rating 1 Very Severe Pilling	Rating	
CC : Cotton Count	Rating 2 Severe Pilling	5	Excellent No Staining
D : Denier	Rating 3 Moderate Pilling	4	Good Slight Staining
F : Fold	Rating 4 Slight Pilling	3	Fair Noticeable Staining
P : Ply	Rating 5 No Pilling	2	Poor Considerable Staining
		1	Very Poor Extensive Staining



Gram Volunteers / Ward Volunteers and Village Secretariats / Ward Secretariats Department, Government of Andhra Pradesh

Continuation Sheet



**REGIONAL LABORATORY
TEXTILES COMMITTEE**
(Ministry of Textiles, Govt. of India)
Textile Testing Services-Quality Cell
Hyderabad



TEST REPORT

(Format No. 12/18/Cp/00)

Test Report No. TC/LH/ST/335/2021-22 Date : 09.09.2021

TEST RESULTS

Lab. Sample No. CCO - 1776

Heat Shrinkage % (IS:11248:95 Annexure-C ('-' Shrinkage; '+' Elongation)	Warp Weft	- 2.5 - 0.80
Water Soluble Matter % (IS:3456:1966 RA 2016)		0.59
pH of Aqueous Extract (pH of dist.H ₂ O 6.97 at 26.2 °C) (IS:1390:1983 RA 2017 cold method)		7.15
Colour Fastness to Washing at 60°C (IS:ISO 105:C10 Test C3 2006 RA 2017) (After 4 Washes)	Change in Colour Staining on Viscose/Polyester	4 4 / 4
Colour Fastness to Rubbing (IS:766:1988 RA 2017)	Dry (Warp/Weft) Wet (Warp/Weft)	4-5 / 4-5 4-5 / 4-5
Colour Fastness to Perspiration (IS:ISO 105:E-04:2008:RA:2019)	Acidic Change in Colour Staining on Viscose/Polyester Alkaline Change in Colour Staining on Viscose/Polyester	4 4 / 4 4 4 / 4
Colour Fastness to Light (xenon arc lamp) (IS:2454:1985 RA 2006)	Blue Wool Rating	5
Colour Fastness to Hot Pressing (IS:689:1988) (Grading immediately and after 4hrs of conditioning)	Change in Colour Dry/Damp/Wet Staining on Cotton Damp/Wet	4 / 4 / 4 4-5 / 4-5



 एम. नारायण
M. NATARAJAN
 सहायक निदेशक (ईपि और कुर)
 Assistant Director (EP&CA)

Signature and Seal of the Officer




Gram Volunteers / Ward Volunteers and Village Secretariats / Ward Secretariats Department, Government of Andhra Pradesh

2. Shirting Cloth



**क्षेत्रीय प्रयोगशाला
वस्त्र समिति**
भारत सरकार, वस्त्र मंत्रालय
सूचना विभाग, पहली मंजिल,
जी.नं. 10-1-1200, ए.सी. गार्ड्स,
मासाब टैंक रोड, हैदराबाद - 4.
टेलिफोन : 040-23327153
ई मेल : hyd.tc@nic.in

**REGIONAL LABORATORY
TEXTILES COMMITTEE**
(Ministry of Textiles, Govt. of India)
Textile Testing Services-Quality Cell
UNI Building, D.No. 10-1-1200, 1st Floor,
A.C. Guards, Masab Tank Road,
Hyderabad - 500 004,
Telefax : 040-23327153
email : hyd.tc@nic.in



TEST REPORT (Format No. 14/18/03)

Test Report No. TC/LH/ST/333/2021-22 **Date :** 09.09.2021

Name and Address of the Customer : The Additional Commissioner (Rural)
O/o Commissioner & Director,
GWWW & VSWs Department, Plot No. 11 & 12,
Nirman Bhavan, APIIC Colony, Vijayawada

Sample forwarding letter No. & Date : 1490545/2021/GSWS, Dated.03.09.2021

Date of receipt of sample : 06.09.2021

Date of performance of tests : 06.09.2021 to 09.09.2021

Customer Sample No.	Sample description as declared by the customer	Sample colour	Lab. Sample No.
	Uniform Cloth -Shirting		CCO-1774

TEST RESULTS

ULRTC92292100000419P

Identification of Fibre (IS:667:1981 RA 2017)		Warp	Polyester + Cotton, Polyester	
		Weft	Polyester	
% Composition (TC/Lab/PTM-02&03) (IS:3416: Part 1:1988 RA 2017) (On Clean dry mass with % additions for moisture)		Polyester	WARP- 85.0	WEFT-100
		Cotton	15.0	----
Breaking Strength of Fabric (Kgf) (IS:1969 Part I 2009 RA 2014) (Ravelled Strip of 5 x 20 cms)		Warp	62.4	
		Weft	53.9	
Count of the yarn removed from fabric(NeC) (TC/LAB/TM-02.Vr.02)		Warp	35.3 ^S (2F)	
		Weft	33.5 ^S (2F)	
Threads/Inch (IS:1963:2004RA:2014)		Warp	50 (Polyester+Cotton), 50 polyester	
		Weft	72	
Mass/Sq.Meter(g) (TC/Lab/TM-03 Vr.02)Cond.			121.5	
Pilling Resistance : (IS:10971:Part I:2011:RA:2017) Avg. Rating			3-4	
Relaxation Shrinkage % (IS:2977:1989 RA 2016) ('-' Shrinkage; '+' Elongation)		Warp	- 0.29	
		Weft	- 0.29	

Bh
9/9/2021
M. NATARAJAN
Assistant Director (TP&O)

(Complaints, if any, are to be received within 45 days of issue of Test Report)

Sample is not drawn by Textiles Committee, results relate only to the above sample/s tested.
This test report is not to be published in any form without the explicit written consent of Textiles Committee.
(Remnant samples will be retained for 90 days from the date of receipt of sample)

Abbreviations	Pilling Rating	Colour Fastness to (Using Grey Scale)		
		Grey Scale Rating	Colour Change	Staining
NeC : English Count	Rating 1	Very Severe Pilling		
Nm : Metric Count	Rating 2	Severe Pilling	5	Excellent
CC : Cotton Count	Rating 3	Moderate Pilling	4	Good
D : Denier	Rating 4	Slight Pilling	3	Fair
F : Fold	Rating 5	No Pilling	2	Poor
P : Ply			1	Very Poor



Gram Volunteers / Ward Volunteers and Village Secretariats / Ward Secretariats Department, Government of Andhra Pradesh

Continuation Sheet



**REGIONAL LABORATORY
TEXTILES COMMITTEE**
(Ministry of Textiles, Govt. of India)
Textile Testing Services-Quality Cell
Hyderabad



TEST REPORT

(Format No. 12/18(C)/00)

Test Report No. TC/LH/ST/333/2021-22 **Date :** 09.09.2021

TEST RESULTS

Lab. Sample No. CCO - 1774

Heat Shrinkage % (IS:11815:86 Appendix-B ('-' Shrinkage; '+' Elongation)	Warp Weft	- 3.8 - 0.40
Water Soluble Matter % (IS:3456:1966 RA 2016)		0.20
pH of Aqueous Extract (pH of dist.H ₂ O 6.97 at 26.2 °C) (IS:1390:1983 RA 2017 cold method)		7.19
Colour Fastness to Washing at 60°C (IS:ISO 105:C10 Test C3 2006 RA 2017)	Change in Colour Staining on Cotton /Polyester	4 4 / 4
Colour Fastness to Rubbing (IS:766:1988 RA 2017)	Dry (Warp/Weft) Wet (Warp/Weft)	4-5 / 4-5 4-5 / 4-5
Colour Fastness to Perspiration (IS:ISO 105:E-04:2008:RA:2019)	Acidic Change in Colour Staining on Cotton /Polyester Alkaline Change in Colour Staining on Cotton /Polyester	4 4 / 4 4 4 / 4
Colour Fastness to Light (xenon arc lamp) (IS:2454:1985 RA 2006)	Blue Wool Rating	5
Colour Fastness to Hot Pressing (IS:689:1988) (Grading immediately and after 4hrs of conditioning)	Change in Colour Dry/Damp/Wet Staining on Cotton Damp/Wet	4-5 / 4 / 4 4-5 / 4-5




Signature and Seal of the Officer

Signature and Seal of the Officer



Gram Volunteers / Ward Volunteers and Village Secretariats / Ward Secretariats Department, Government of Andhra Pradesh

3. Bottom Cloth

 శ్రీలక్ష్మీ ప్రయోగశాల వస్త్ర సమితి भारत सरकार, वस्त्र मन्त्रालय मूलनगरा सिविलिंग, पहलिसि मणिस, को.नं. 10-1-1200, एसी गार्डस, माराब टैंक रोड, हैदराबाद - 4, टेलिफोनस : 040-23327153 ई मेल : hyd.to@nrc.in	REGIONAL LABORATORY TEXTILES COMMITTEE (Ministry of Textiles, Govt. of India) Textile Testing Services-Quality Cell UNI Building, D.No. 10-1-1200, 1st Floor, A.C. Guards, Masab Tank Road, Hyderabad - 500 004, Telefax : 040-23327153 email : hyd.to@nrc.in				
TEST REPORT (Format No. 14/18/03)					
Test Report No. TC/LH/ST/334/2021-22		Date : 09.09.2021			
Name and Address of the Customer : The Additional Commissioner (Rural), O/o Commissioner & Director, GVW & VSW Department, Plot No. 3, 1 & Nirman Bhavan, APIIC Colony, Vijaya vad,					
Sample forwarding letter No. & Date : 1490545/2021/GSWS, Dated.03.09.2021					
Date of receipt of sample : 06.09.2021					
Date of performance of tests : 06.09.2021 to 09.09.2021					
Customer Sample No.	Sample description as declared by the customer	Sample colour	Lab. Sample No.		
	Uniform Cloth -Pyzama (Female)		CCO-1775		
TEST RESULTS					
ULRTC92292100000420P					
Identification of Fibre (IS:667:1981 RA 2017)		Warp Weft	Polyester + Viscose Polyester + Viscose		
% Composition (TC/Lab/PTM-02&03) (IS:3416: Part 1:1988 RA 2017) (On Clean dry mass with % additions for moisture)		Polyester Viscose	WARP- 70.0 30.0 WEFT- 70.2 29.8		
Breaking Strength of Fabric (Kgf) (IS:1969 Part I 2009 RA 2014) (Ravelled Strip of 5 x 20 cms)		Warp Weft	77.2 79.4		
Count of the yarn removed from fabric(NeC) (TC/LAB/TM-02.Vr.02)		Warp Weft	19.0 ^S (2F) 18.6 ^S		
Threads/inch (IS:1963:2004RA:2014)		Warp Weft	62 56		
Mass/Sq.Meter(g) (TC/Lab/TM-03 Vr.02)Cond.			158.9		
Pilling Resistance :(IS:10971:Part I:2011:RA:2017) Avg. Rating			4		
Relaxation Shrinkage % (IS:2977:1989 RA 2016) ('-' Shrinkage; '+' Elongation)		Warp Weft	- 0.57 - 0.77		
 M. NATARAJAN Director (Quality & Control)					
(Complaints, if any, are to be received within 45 days of issue of Test Report)					
Sample is not drawn by Textiles Committee, results relate only to the above sample/s tested. This test report is not to be published in any form without the explicit written consent of Textiles Committee. (Remnant samples will be retained for 90 days from the date of receipt of sample)					
Abbreviations		Pilling Rating		Colour Fastness to (Using Grey Scale)	
NeC : English Count	Rating 1	Very Severe Pilling	Grey Scale Rating	Colour Change	Staining
Nm : Metric Count	Rating 2	Severe Pilling	5	Excellent	No Staining
CC : Cotton Count	Rating 3	Moderate Pilling	4	Good	Slight Staining
D : Denier	Rating 4	Slight Pilling	3	Fair	Noticeable Staining
F : Fold	Rating 5	No Pilling	2	Poor	Considerable Staining
P : Ply			1	Very Poor	Extensive Staining



Gram Volunteers / Ward Volunteers and Village Secretariats / Ward Secretariats Department, Government of Andhra Pradesh

Continuation Sheet



**REGIONAL LABORATORY
TEXTILES COMMITTEE**
(Ministry of Textiles, Govt. of India)
Textile Testing Services-Quality Cell
Hyderabad



(Formal No. 12/18/C/00)

TEST REPORT

Test Report No. TC/LH/ST/334/2021-22 Date : 09.09.2021

TEST RESULTS

Lab. Sample No. CCO - 1775


Heat Shrinkage % (IS:11815:86 Appendix-B (*Shrinkage; + Elongation)	Warp	- 2.2
	Weft	- 1.6
Water Soluble Matter % (IS:3456:1966 RA 2016)		0.30
pH of Aqueous Extract (pH of dist.H ₂ O 6.97 at 26.2 °C) (IS:1390:1983 RA 2017 cold method)		7.10
Colour Fastness to Washing at 60°C (IS:ISO 105:C10 Test C3 2006 RA 2017)	Change in Colour	4
	Staining on Viscose/Polyester	4 / 4
Colour Fastness to Rubbing (IS:766:1988 RA 2017)	Dry (Warp/Weft)	4-5 / 4-5
	Wet (Warp/Weft)	4 / 4
Colour Fastness to Perspiration (IS:ISO 105:E-04:2008:RA:2019)	Acidic Change in Colour	4
	Staining on Viscose/Polyester	4 / 4
	Alkaline Change in Colour	4
	Staining on Viscose/Polyester	4 / 4
Colour Fastness to Light (xenon arc lamp) (IS:2454:1985 RA 2006)	Blue Wool Rating	5
Colour Fastness to Hot Pressing (IS:689:1988) (Grading immediately and after 4hrs of conditioning)	Change in Colour Dry/Damp/Wet	4-5 / 4 / 4
	Staining on Cotton Damp/Wet	4-5 / 4-5

Signature and Seal of the Officer



Gram Volunteers / Ward Volunteers and Village Secretariats / Ward Secretariats Department, Government of Andhra Pradesh


4. Chunny Cloth



क्षेत्रीय वस्त्रसमिति
वस्त्र समिति

भारत सरकार, वस्त्र मन्त्रालय
पूरुनय्यु बिल्डिंग, पश्चिम बंगाल,
खो.नं. 10-1-1200, एसी गार्ड्स,
मास्ब टैंक रोड, हैदराबाद - 4
टेलिफोन नं. : 040-23327153
ई मेल : hyd.to@nic.in

REGIONAL LABORATORY
TEXTILES COMMITTEE
(Ministry of Textiles, Govt. of India)
Textile Testing Services-Quality Cell
UNI Building, D.No. 10-1-1200, 1st Floor,
A.C. Guards, Masab Tank Road,
Hyderabad - 500 004,
Telefax : 040-23327153
email : hyd.to@nic.in



(Formal No. 14/18/G/3)

TEST REPORT

Test Report No. TC/LH/ST/336/2021-22 **Date :** 09.09.2021

Name and Address of the Customer : The Additional Commissioner (Rural)
O/o Commissioner & Director,
GWW & VSWS Department, Plot No. 1,
Nirman Bhavan, APIIC Colony, Vijayawada

Sample forwarding letter No. & Date : 1490545/2021/GSWS, Dated.03.09.2021

Date of receipt of sample : 06.09.2021

Date of performance of tests : 06.09.2021 to 09.09.2021

Customer Sample No.	Sample description as declared by the customer	Sample colour	Lab. Sample No.
	Uniform Cloth -Dupatta		CCO-1777

TEST RESULTS

ULRTC922921000000422F

Dimensions: (IS:1954:1990 RA 2017)	Length	2.0 m
	Width	81.2 cm
Count of the yarn removed from fabric (TC/LAB/TM-02 Vr.02)	Warp	84.1 D
	Weft	86.2 D
Identification of Fibre (IS:667:1981 RA 2017)	Warp	Polyester
	Weft	Polyester
% Composition	Polyester	100
Colour Fastness to Washing at 60°C (IS:ISO 105:C10 Test C3 2006 RA 2017)	Change in Colour	4
	Staining on Cotton/Polyester	4 / 4
Colour Fastness to Perspiration (IS:ISO 105 E-04:2008:RA:2019)	Acidic Change in Colour	4 *
	Staining on Cotton/Polyester	4 / 4
	Alkaline Change in Colour	4
	Staining on Cotton/Polyester	4 / 4
Colour Fastness to Rubbing (IS:766:1988 RA 2017)	Dry (Warp/Weft)	4-5 / 4-5
	Wet (Warp/Weft)	4-5 / 4-5
Colour Fastness to Light (xenon arc lamp) (IS:2454:1985 RA 2008)	Blue Wool Rating	5

Signature and Seal of the Officer
एम. नारायण
NE NARAYAN

(Complaints, if any, are to be received within 45 days of issue of Test Report)

Sample is not drawn by Textiles Committee, results relate only to the above sample/s.
This test report is not to be published in any form without the explicit written consent of Textiles Committee.
(Remnant samples will be retained for 90 days from the date of receipt of sample)

Abbreviations	Pilling Rating		Colour Fastness to (Using Grey Scale)		
	Rating	Description	Grey Scale Rating	Colour Change	Staining
NeC : English Count	Rating 1	Very Severe Pilling	5	Excellent	No Staining
Nm : Metric Count	Rating 2	Severe Pilling	4	Good	Slight Staining
CC : Cotton Count	Rating 3	Moderate Pilling	3	Fair	Noticeable Staining
D : Denier	Rating 4	Slight Pilling	2	Poor	Considerable Staining
F : Fold	Rating 5	No Pilling	1	Very Poor	Extensive Staining
P : Ply					